Prüfbericht - Nr.: *Test Report No.:*	**IND/BLR/CH/2017/0398**	**Seite 1 von 2** *Page 1 of 2*

Auftraggeber: *Client:*	**SUNFLEX RUBBER** Plot No. 274/4 , Shital Estate, B/H Satyamev Complex, Opp. Gujarat High Court, S.G. Highway, Sola, Ahmedabad - 380060,Gujarat, India
Gegenstand der Prüfung: *Test item:*	Interlocking Rubber Tiles

Bezeichnung: *Identification:*	-	**Serien-Nr.:** *Serial No./* Document Submitted*:*	Letter Dated: 23.12.2016
Wareneingangs-Nr.: *Receipt No.:*	24012017	**Eingangsdatum:** *Date of receipt:*	24.01.2017
Order No.:	1803199867	*Testing Period:*	24.01.2017 to 21.02.2017

Prüfort: *Testing location:*	TÜV Rheinland India Pvt Ltd, Plot No.17B, Electronic City Phase II Industrial Area, Hosur Road, Bangalore - 560 100, Karnataka, India
Prüfgrundlage: *Test specification:*	Customer's requirement : Testing for specified Chemical Parameters
Prüfergebnis: *Test Result:*	Refer to the following page (s). 2 to 2

Prüflaboratorium/ Testing Laboratory:

zusammengestellt/ *compiled by*:		**kontrolliert/***checked by:*	
21.02.2017	Chandrashekara Aithala B Sr. Manager - Industry Services	21.02.2017	Rajesh Jain. B Technical Head, Material Testing Laboratories, Industry Services
Datum *Date*	**Name** *Name*	**Unterschrift** *Signature*	**Datum** *Date*	**Name** *Name*	**Unterschrift** *Signature*

Sonstiges/ Other Aspects: NIL

Abkürzungen:	***ok / P***	***= entspricht Prüfgrundlage***	***Abbreviations:***	***ok / P***	***= passed***
	fail / F	***= entspricht nicht Prüfgrundlage***		***fail / F***	***= failed***
	n.a. / N	***= nicht anwendbar***		***n.a. / N***	***= not applicable***

Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens.

This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

Prüfbericht - Nr.: **IND/BLR/CH/2017/0398** **Seite 2 von 2**
Test Report No.: *Page 2 of 2*

TEST RESULTS

Sample Description	Interlocking Rubber Tiles
Sampling : 1. Submitted Sample drawn by the laboratory : No (If yes please provide the sampling reference)	

Sl no	Parameter	Unit	Result	Test Method
1	Hardness Shore	-	59	ASTM D 2240
2	Density	Kg/m^3	1.0	ASTM D 792
3	Tensile Properties (After Aging at 70^0C for 72 hrs) Tensile Strength	MPa	1.01	ASTM D573/ASTM D412
	Elongation at Break	%	47	ASTM D573/ASTM D412
4	Ground Electrical Resistance	M ohms	168	ASTM F 150
5	Tensile Properties (As received) Tensile Strength	MPa	0.85	ASTM D412
	Elongation at Break	%	41	ASTM D412
6	Skid Resistance (Dry Condition)	-	40	ASTM E 303

Note:

Test Item Photograph:

---- End of Test Report ----